

STONES			
ST-001	Sima 2103 Calisco Quartz Stone	<p>Natural stone must have a static coefficient of friction SCOF (ASTM-C1028-07e1; www.astm.org) of 0.6 wet or better or Dynamic Coefficient of Friction DCOF (ASTM-A137.1) of .42 or better.</p> <p>2514.03.D.2 Any natural porous materials must be sealed after installation with a penetrating non-glossy sealer.</p> <p>2514.03.D.3 Natural stone must be rectilinear, gauged with a micro-bevel.</p> <p>2514.03.E Grout</p> <p>2514.03.E.1 Natural stone grout must be non-shrink-type epoxy or latex portland cement to minimize staining and the minimum grout joint should comply with ISO or ANSI guidelines. 1/16" /1.6 mm is the maximum width allowed.</p> <p>2514.03.E.2 Cementitious grout must be sealed after installation.</p> <p>All porous stone tops must be properly sealed upon installation. The use of a tuff skin sealer or an equivalent is required</p>	